



PET DTF FILM
白墨烫画膜




saillagedtf.com



TD9002 Hot/Cold Peel Double Sided DTF FILM

TD9002 is a premium extra-thick DTF PET film made with a 95 μm PET base film. Its enhanced stiffness provides excellent feeding stability, heat resistance, and dimensional stability, helping reduce skewing, wrinkling, and deformation during production. It is especially suitable for high-speed printing, continuous operation, and high ink-load applications that require reliable and consistent performance.



A: Ink absorption , water-based, 100% ink loading

B: Release layer, water-based coating, eco-friendly

C: PET film, 100% pure, offers both mechanical strength and heat resistance

D: Back coating, Anti-slip, Anti-static, Anti-adhesion, Anti-blocking and scratch-resistant.

1. Basic Information

a. Product Name: TD9002 Hot/Cold Peel Double Sided DTF FILM FOR TEXTILE

b. Product Code: SL-TD9002

c. Type: Premium

d. Material: 95um PET

e. Surface: Matte

f. Thickness: 103±3 um

g. Peel Type: Hot & Cold

h. Width: 30/33/42/60/62/80/90/120/160cm , customzied

i. Length: 100/200/300/500m, customized

2. Key Specification

①Excellent feeding stability

②Excellent heat resistance

③Excellent dimensional stability

④Anti-static and Anti-slip Performance

⑤Vibrant Color

⑥High Ink-loading Capacity

⑦No Oil Migration or Moisture Bleeding

3. Coating Performance

a. Ink Loading: 100%

b. Coating Uniformity: Uniform

c. Drying Performance: Fast Dry

d. Anti-static: Yes

e. Anti-slip: Yes

f. Powder Adhesion: No

4. Printing performance

a. Printer Compatibility: Compatible with most DTF printers

b. Printhead Compatibility: Epson I3200 / 4720 / XP600 etc

c. Ink Compatibility: Water-based pigment DTF ink

d. Feeding Performance: Smooth and stable

e. Tracking Stability: Excellent

- f: Wrinkle Resistance:** Excellent
- g: Edge Curl Resistance:** Excellent
- h: Continuous Printing:** Excellent

5. Curing performance

- a. Recommended curing temperature: 110–130°C
- b. Recommended curi
- c. Good heat resistance and dimensional stability
- d. Low thermal shrinkage during curing
- e. Maintains good flatness under continuous heating
- f. Reduced risk of curling, wrinkling and deformation
- g. Stable coating performance during powder melting
- h. Compatible with standard DTF hot-melt adhesive powders
- i. Suitable for continuous curing and mass production

6. Heat Press Performance

Test Item	Test Result
Release Performance	Smooth and complete release
Fine Line Transfer	Good
Small Letter Transfer	Good
Color Reproduction	Bright and accurate
White Ink Coverage	Good
Peel Residue	No
Re-press Compatibility	Yes

7. Wash Performance

Test Item	Test Result
Wash Resistance	40°C > 30
Color Change	No
Cracking	No
Peeling	No

* Final wash durability depends on the complete DTF printing system and processing conditions.


8. Application

Suitable for heat transfer printing on cotton, polyester, blended fabrics, garments, bags, caps and other textile products.

9. Storage and Shelf-life

- a. Storage Temperature: 15–30°C
- b. Relative Humidity: 40–70% RH
- c. Storage Method: Keep sealed in original packaging
- d. Avoid: Direct sunlight, heat, moisture, dust and pressure
- e. Shelf Life: 12 months

THE PROCESS



Statement and Disclaimer: The information provided in this Technical Data Sheet is based on current laboratory testing and production experience. It is intended as a general reference only and does not constitute a guarantee for all applications. Customers should conduct their own testing before commercial use.



PET DTF FILM
白墨烫画膜

